

K Material






μ_i 1500 \pm 25%

Saturation Flux Density - gauss 4600 (at 15 oersted, 25°C) (460 mT)

Coercive Force - oersted 0.2 (16A/m)

Curie Temperature 230°C

Note: The core loss curves are developed from empirical data. For best results and highest accuracy, use them. The formula on page 2.11 yields a fair approximation and can be useful in computer programs.



See Page 2.12 for B-H Data